

POLYETHYLENE PE 2260M (601F7)

Product obtained by gas-phase polymerization of ethylene in presence of complex metalorganic catalysts.

Stabilization recipe: antacid, antioxydant, heat stabilizer, processing additive, dispersant

Application: blow molding of products with volume max 0,5 dm³.

Polyethylene type:

Chemical

name:

Empirical

formula:

Technical requirements:

High density polyethylene(HDPE)

Ethylene homopolymer

(-CH₂-CH₂-)_n

TU 2211-145-05766801-2008

PROPERTY	Value	TEST METHOD
1. Density (base polymer), g/cm ³ , in the range	0.958 – 0.962	ASTM D 1505
2. Melt flow rate, g/10 min, in the range - at 190°C and 5,0 kg - at 190°C and 2,16 kg	- 0.4– 0.9	ASTM D1238/L
3. Melt flow rate ratio: - MFR _{21,6 kg} /MFR _{5,0 kg} - MFR _{21,6 kg} /MFR _{2,16 kg}	- above 50	ASTM D 1238

Additional reference ratings

PROPERTY	VALUE	Test method
1. Flexural modulus, MPa, min:	1400	ASTM D 790
2. Izod impact strength at 23°C, J/m, min	120	ASTM D 256

Supply form: Pellets

Packaging: Product is packed into polyethylene bags (one bag net weight 25.00 ± ±0.25 kg) and bundled on flat pallets with shrink film. Gross weight of a bundle is max 2 t. PE may be packed into soft containers (big bags) sized for 400-1000 kg. Upon agreement with Customer PE pellets are bulk loaded into railway cars, tipper trucks or loaded in bags to railway cars.

Transportation: By all transport means.

Storage: Polyethylene shall be stored in enclosed dry space preventing from direct sun rays, on shelves or pallets at least 5 cm from the floor, and at least 1 m from heaters, at temperature max 30°C and relative humidity max 80%.
Prior to processing, bags with polymer shall be kept for at least 12 hrs in production area.

Information contained herein is provided to the best of our knowledge and is considered true on the revision date. This specification does not release customer from the responsibility to check the product for suitability for the intended use. Manufacturer bears no liability for any loss and damage which may occur due to use of this information.

www.nknh.ru